

Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) **EP 0 984 045 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
08.03.2000 Bulletin 2000/10

(51) Int. Cl.⁷: **C09D 11/00, C09D 11/10,
C09B 67/00, C09B 69/00**

(21) Application number: **98116822.2**

(22) Date of filing: **04.09.1998**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

• **Schwartz, Russell**
Cincinnati, Ohio 45232 (US)
• **Chatterjee, Subhankar**
Hampton, New Jersey 08827 (US)
• **Merchak, Paul A.**
Loveland, Ohio 45140 (US)

(71) Applicant: **SUN CHEMICAL CORPORATION**
Fort Lee, NJ 07024 (US)

(74) Representative:
VOSSIUS & PARTNER
Siebertstrasse 4
81675 München (DE)

(72) Inventors:
• **Laksin, Mikhail**
Scotch Plains, New Jersey 07076 (US)

(54) **Energy curable inks incorporating grafted pigments**

(57) Solvent-free, energy curable low viscosity printing inks which contain a pigment; a rheological additive; an energy curable liquid vehicle which may be a cationic or a free radical initiated polymerization

system, cured by actinic radiation; and optionally a photoinitiating system. The rheological additive has the structure P-(U-Y), wherein P is the residue of an organic pigment or dye, Y is a polyalkylene oxide moiety, U is a linking moiety covalently bonding Y to P and s is an integer from 1 to 3.

EP 0 984 045 A1

Description

[0001] This invention relates to low viscosity inks for use in printing. More particularly, the invention relates to inks which are energy curable by electron beams (EB) or ultraviolet (UV) radiation and the like.

5 [0002] Low viscosity and good flow are the most important factors affecting liquid ink behavior and improved printability. These factors are particularly important for formulating inks for gravure and flexographic printing. Schwartz et al. in U.S. Patent 4,468,255, disclose rheology modifiers for arylide yellow pigment dispersions. The rheology modifiers which are derived from diarylide pigments improve the fluidity of non-aqueous arylide pigment dispersions prepared from either monoarylide or diarylide yellow pigments. Schwartz et al. in a series of patents
10 (i.e., U.S. Patents 4,946,508; 4,946,509; 5,024,698; and 5,062,894) have disclosed modified azo pigments for use in conventional, solvent and water based inks and coatings to function as rheology control agents. In each of these patents, Schwartz et al. modify an azo pigment (e.g., a diarylide pigment, a monoazo pigment, a disazo pyrazolone pigment and the like) by grafting a polyalkylene oxide to the pigment so that water based inks made from these pigment compositions exhibit high coloring strength, cleaner shades, lower rheology, and enhanced gloss compared with
15 conventional water based inks.

[0003] To increase printing throughput, UV or EB curable inks have been developed that allow printers to reduce the solvent content of the ink. It is always a challenging task for a UV or EB curable liquid ink formulator to develop ink formulations with a viscosity low enough for improved flow, while at the same time maintaining other essential characteristics, such as to cure, adhesion, low odor, etc. Traditional organic and inorganic pigments used
20 in formulating energy curable liquid inks, are poorly dispersed in the vehicles used in the systems. As a result, poor pigment wetting leads to a thixotropic structure. If the inks are not subjected to high shear, the apparent viscosity will remain high and the ink will exhibit poor transfer resulting in poor printability. Flow additives have been tried, however, with limited success for different pigments. The situation becomes more critical in the case of cationic curable inks, where not all the pigments and additives can be used due to the presence of basic functionalities. In addition, some energy curable inks of the prior art contain fugitive solvent (such as water,
25 alcohols and the like) as part of the vehicle to reduce viscosity, aid in pigment dispersion, and modify flow during printing. However, after printing but before curing, the fugitive solvent is typically removed to prevent interference with the curing process and to prevent it from having an adverse affect on the printed image. The curing delay required by solvent removal, as well as attendant unpleasant odors, are further undesirable limitations to printing. Furthermore, solvent removal is desirable for environmental reasons.

[0004] A UV-cured cationically polymerized printing ink is disclosed by Seng in Patent Application DE 195 00 968.1 for use in indirect letterpress printing or dry offset printing. Seng lists the differences between letterpress and flexographic printing and the list includes critical differences in ink viscosities. In particular, Seng discloses that printing inks used in flexographic printing have viscosities in the range of 0.01 to 2 Pa·s and
35 at 20°C in the range of 3.0 to 100.0 Pa·s, and more preferably in the range of 4.0 to 10 Pa·s. Seng's inks are cationically polymerized and differ from the very high viscosity printing inks used in indirect letterpress printing in solvent content. While inks of this viscosity range are useful in high shear, indirect letterpress printing, such inks have high tack which causes them to be unsuitable for low shear applications such as flexography, which requires low tack inks.

40 [0005] Although improvements have been made in energy curable, cationic ink formulations, there continues to be a need for energy curable ink formulations (including free radical initiated curable formulations) which have a high color strength, cleaner shade and enhanced gloss but retain a very low viscosity as required by certain modes of printing.

[0006] The invention is an energy curable ink comprising a pigment, a Theological additive having the structure:



wherein P is the residue of an organic colorant, Y is a polyalkylene oxide moiety, U is a linking moiety covalently bonding Y to P and s is an integer from 1 to 3; and an energy curable liquid vehicle; wherein the ink is
50 substantially free of fugitive solvent.

[0007] In another embodiment of this invention, this energy curable ink further comprises a polymerization initiating system activatable by actinic radiation.

[0008] In yet a further embodiment of this invention there is a method of printing and curing an ink comprising the steps:

55 (I) providing the energy curable ink described supra;

(II) printing the ink onto a substrate surface to form the ink image; and

(III) subjecting the ink image to actinic radiation or thermal energy to form a cured ink image.

[0009] The present invention is directed to a novel solvent-free, energy curable ink for use in printing applications which require low to very low viscosity inks. The term "energy curable or cured" as used herein, in reference to ink means an ink which can be cured, hardened, polymerized, or crosslinked by the action of actinic radiation such as UV or EB radiation and the like from a radiant energy source; or from a thermal energy source by heating with a conductive or radiant heat source such as a platen, an oven, infrared (IR), microwave, and the like.

[0010] The energy curable ink of this invention comprises a pigment composition and an energy curable liquid vehicle is substantially free of a fugitive solvent. The terms "substantially free of fugitive solvent" and "solvent-free", as used herein in reference to inks, means free of a liquid component (e.g., water, lower alcohols, alkanes, aromatics, aliphatics, ketones, acetates and the like) which, after printing, is evaporated, imbibed into a substrate surface, or both, and does not remain as an essential component of the cured ink. Further, these terms are not intended to exclude trace or residual solvents resulting from the manufacture of ink components prior to ink formulation.

[0011] The term "colorant", as used herein means an organic pigment or dyestuff. The energy curable liquid vehicle typically comprises one or more low molecular weight mono- or multi-functional monomers. For offset inks and other inks which require higher viscosities, a resin, a reactive oligomer or polymer may also be present. The inks of the present invention may be cured thermally or by actinic radiation sources, such as electron beams and the like; or photolytically cured by actinic radiation, such as UV radiation and the like, when a suitable initiating system is incorporated into the ink. The solvent-free, energy curable inks of this invention are more fully described in the following examples.


Pigment

[0012] The pigment is any organic pigment that can be employed for the coloration of conventional printing inks of the prior art. The pigment may also be carbon black. Pigments suitable for use in the present invention may be any conventional organic pigment such as: Pigment Yellow 1, Pigment Yellow 3, Pigment Yellow 12, Pigment Yellow 13, Pigment Yellow 14, Pigment Yellow 17, Pigment Yellow 37, Pigment Yellow 63, Pigment Yellow 65, Pigment Yellow 73, Pigment Yellow 74, Pigment Yellow 75, Pigment Yellow 83, Pigment Yellow 97, Pigment Yellow 98, Pigment Yellow 106, Pigment Yellow 114, Pigment Yellow 121, Pigment Yellow 126, Pigment Yellow 127, Pigment Yellow 136, Pigment Yellow 174, Pigment Yellow 176, Pigment Yellow 188, Pigment Orange 5, Pigment Orange 13, Pigment Orange 16, Pigment Orange 34, Pigment Red 2, Pigment Red 9, Pigment Red 14, Pigment Red 17, Pigment Red 22, Pigment Red 23, Pigment Red 37, Pigment Red 38, Pigment Red 41, Pigment Red 42, Pigment Red 112, Pigment Red 146, Pigment Red 170, Pigment Red 196, Pigment Red 210, Pigment Red 238, Pigment Blue 15, Pigment Blue 15:1, Pigment Blue 15:2, Pigment Blue 15:3, Pigment Blue 15:4, Pigment Green 7, Pigment Green 36, Pigment Violet 23, or carbon black, including Pigment Black 7 and the like.

Rheological Additive

[0013] The rheological additive is a polyalkylene oxide covalently bonded (i.e. grafted) to the residue of an organic colorant and has the structure: $P-(U-Y)_s$, in which P is the residue of an organic colorant, Y is a polyalkylene oxide moiety preferably containing about 4 to about 400 alkylene oxide repeat units, and U is a linking moiety covalently bonding Y to P and s is an integer from 1 to 3. Typically, P is a residue of a pigment, such as, a residue of an azo pigment, phthalocyanine pigment, dioxazine pigment, quinacridone pigment, perylene pigment, perinone pigment or the like. Preferably, P is the residue of a diarylide pigment, monoazo pigment, disazo pyrazolone pigment, phthalocyanine pigment, or perylene pigment.

[0014] The polyalkylene oxide moiety, Y, may be the residue of any polyalkylene oxide such as an ethylene oxide polymer, an ethylene oxide/propylene oxide copolymer and the like. Preferably, Y is an alkylene oxide copolymer having the general formula:




wherein n is about 4 to about 400 and more preferably is about 4 to about 60; each Q is independently H or CH₃

and Q' is a C₁-C₆ alkyl moiety. The weight average molecular weight of the polyalkylene oxide moiety typically is between about 300 and 3,600; and preferably between about 1,000 and 3,000. The polyalkylene oxide moiety, Y, may be grafted to the residue of an organic colorant, P, through a linking moiety, U, which is preferably a covalent bond or multivalent moiety such as C₁-C₆ alkyl, -NHSO₂-, -O-, -CO-, -COO-, -N-, -CONH-, and the like. It is understood that the particular linking moiety employed will be determined by those skilled in the art depending on the nature of P.

[0015] Combinations of pigment and rheological additive particularly useful in the solvent free energy curable inks of the invention are described in U.S. Patents 4,946,508; 4,946,509; 5,024,698; and 5,062,894; each of which is incorporated herein by reference.

[0016] In particular, Schwartz et al, U.S. Patent 4,946,508 discloses disazo pyrazolone compositions which contain said rheological additives and their method of manufacture. Such disazo pyrazolone pigment compositions have the general formula:


Formula I



wherein Y is the polyalkylene oxide moiety; R^{1a} is H, CH₃, OCH₃, OCH₂CH₃ or Cl; n is selected from an integer from 1 to 5; R^{2a} is CH₃ or COOCH₂CH₃; R^{3a} is H or CH₃; and X^{1a} is Cl or OCH₃

[0017] U. S. Patent 4,946,509, Schwartz et al discloses azomethine compositions and their method of manufacture. Such azomethine pigment compositions have the general formula:


Formula II



wherein Y is the polyalkylene oxide moiety containing about 4 to about 200 groups; R and R^{1a} are independently selected from the group consisting of H, CH₃, OCH₃, OCH₂CH₃ and Cl; n is selected from an integer from 1 to 5; X is selected from the group consisting of Cl, CH₃, and OCH₃; and Z is selected from O and N-Y.

[0018] U.S. Patent 5,024,698, Schwartz et al discloses monoazomethine compositions and their method of manufacture. Such monoazomethine pigments have the general formula:


Formula III



wherein Y is the polyalkylene oxide moiety; R^{6a} is independently selected from the group consisting of Cl, OCH_3 , CH_3 , OC_2H_5 , C_2H_5 , and $CONH_2$; R^{7a} is independently selected from the group consisting of Cl, OCH_3 , CH_3 , NO_2 , OC_2H_5 , C_2H_5 , $CONH_2$, SO_3H , OH and COOH; and a and b are independently selected from integers 0 to 5.

[0019] U.S. Patent 5,062,894, Schwartz et al discloses diarylide compositions and their method of manufacture. Such diarylide pigment compositions have the general formula:


Formula IV




wherein R^{4a} and R^{5a} are independently selected from the group consisting of C_1 - C_4 alkyl, C_1 - C_4 alkoxy, and halogen; m and p are independently selected from integers of 0 to 5; X^{2a} is selected from the group consisting of Cl, CH_3 , and OCH_3 ; U^{2a} comprises a divalent bridging moiety selected from the group consisting of C_1 - C_8 alkyl, $-NHSO_2-$, $-O-$, $-CO-$, $-COO-$, and $-CONH-$; Y^{1a} comprises the polyalkylene oxide moiety having a number average molecular weight of about 200 to 10,000; and k and l are independently selected from integers 0 or 1, with the proviso that for at least 50 wt.% of the composition, k and l are both 0, and for at least 3 wt.% of the composition k and/or l are 1.

[0020] Other rheological additives particularly useful in the energy curable inks of this invention, include phthalocyanine compositions having the P-U-Y structure in which P, is the residue of a copper phthalocyanine pigment and wherein the linking moiety, U, is $-NHSO_2-$ which joins P to Y. Such copper phthalocyanine based rheological additives have the general formula:

Formula V



wherein Y is a polyalkylene oxide moiety which has the general formula:



wherein n is about 4 to about 400, and a, b, c and d are integers independently from 0 to 4, provided at least one of them is 1; Q is selected from H, CH₃ or a combination thereof; and Q' is a C₁-C₆ alkyl moiety.

[0021] The rheological additive used in this invention may be prepared by any conventional method. Illustrative methods for preparing the pigments with the rheological additives described herein are disclosed in U.S. Patents 4,946,508; 4,946,509; 5,024,698; and 5,062,894 and in the examples.

[0022] The pigment compositions used in this invention typically contain a minor portion of said rheological additive and a major portion of the conventional pigment. The residue of the organic colorant that is contained in the rheological additive does not need to be of the same type as the pigment of the ink formulation. For example, the additive of Formula V may be utilized with Pigment Violet 23 or Pigment Black 7.

[0023] An advantage of the preparation methods disclosed in the Schwartz et al. patents supra, is that a blend of the colorant additive and the pigment is produced directly, and may be used without further blending. To produce printing inks with a desired hue, a separate pigment may be added which is distinct from the pigment and rheological additive. Methods of effecting a desired hue from precursor pigments are well known to the ink formulator and are illustrated in the examples.

Energy Curable Liquid Vehicle

[0024] The solvent-free, energy curable ink of this invention contains as the third essential component a quantity of an energy curable liquid vehicle which is substantially free of fugitive solvent. The quantity of liquid vehicle employed is an amount sufficient to make up 100% of the ink weight when taken together with other ink components. The radiation curable liquid vehicle typically comprises one or more low molecular weight mono-functional or multi-functional monomers. For offset inks and other inks which require higher viscosities, a resin, a reactive oligomer or polymer may also be present. These components may react with the monomers upon curing. The energy curable liquid vehicle is characterized in that it is curable to a solid by exposure to energy from a radiant or thermal energy source as described supra. The liquid vehicle may be cured to a solid by exposure to energy, such as exposure to high energy electrons from an electron beam source. Alternatively, curing of the liquid vehicle may be initiated by energy activation of a polymerization initiating system (e.g., by UV radiation) as will be described in detail hereinbelow. In this context, a polymerization initiating system may be considered an optional component of the energy curable liquid vehicle. The liquid vehicle may be a ring opening polymerizable composition, a free radical addition polymerizable composition, or by a combination of ring opening and free radical polymerization. In

either composition, the liquid vehicle is cured or hardened by polymerizing and/or crosslinking, at least the reactive monomers of the liquid vehicle. In order to reduce environmental contamination and maintain formulation integrity, the liquid vehicle is typically formulated with components having low volatility under ambient printing conditions.

5 [0025] When the liquid vehicle is a ring opening polymerizable composition, upon energy initiation it forms a polymer typically bound by ester, or ether linkages.

[0026] In a preferred embodiment of the invention the polymerizable composition is a cationic polymerizable system comprising one or more mono-functional or multi-functional epoxides. The liquid vehicles typically contain at least one cycloaliphatic epoxide. Examples of such cycloaliphatic epoxides are adducts of epoxides and hydroxyl components such as glycols, polyols, or vinyl ether, such as 3,4-epoxycyclohexylmethyl 3,4-epoxycyclohexane carboxylate; bis(3,4-epoxycyclohexylmethyl)adipate; limonene monoepoxide; limonene diepoxide; diglycidyl ester of hexahydrophthalic acid; 1-vinyl-3,4-epoxycyclohexane; epoxidated dicyclopentyl alcohol; or a mixture thereof. A preferred cycloaliphatic epoxide of this type is 3,4-epoxycyclohexylmethyl -3,4-epoxycyclohexylcarboxylate. In addition to the cycloaliphatic epoxides there may be one or more noncycloaliphatic epoxides, such as di- or tri-glycidyl ether, alkoxylated bisphenol A, 1,6-hexane diol, glycerol; neopentylglycol; or trimethylolpropane. The epoxy diluent likewise may be diglycidyl ether of bisphenol A; an alpha-olefin epoxide, a Novalac epoxide, epoxidated linseed oil, soy oil; epoxidated polybutadiene; 1,2-epoxydecane; caprolactone triol; glycidyl ether; alkyl glycidylether; epoxidated silanes; 2-ethylhexylglycidyl ether. In such epoxy compositions, the ink typically contains a cationic initiating system activatable by actinic radiation as will be described hereinbelow.

20 and the like. A preferred epoxy diluent is 2-ethylhexylglycidyl ether. In such epoxy compositions, the ink typically contains a cationic initiating system activatable by actinic radiation as will be described hereinbelow.

[0027] When the energy curable liquid vehicle is a free radical addition polymerizable composition, the vehicle comprises a liquid compound having terminal ethylenic unsaturation.

25 [0028] Typically, the liquid vehicle is a free radical addition polymerizable system comprising an ethylenically unsaturated mono- or multi-functional monomer. The monomer is a lower molecular weight ethylenically unsaturated compound which forms a polymer directly upon initiation by free radicals generated by absorbed energy. In some formulations an oligomeric or polymeric component which can be further polymerized may also be present. In such cases the further polymerizable material will be soluble in, or dispersible in the monomer vehicle.

30 [0029] Typically, the monomeric compounds have one, two, or more terminal ethylenically unsaturated groups. Representative of such monomeric compounds are: N-vinyl pyrrolidinone; dipropylene glycol diacrylate; tripropylene glycol diacrylate; butanediol diacrylate; hexanediol diacrylate; trimethylol propane triacrylate; ethoxylated trimethylol propane triacrylate; glycerolpropoxy triacrylate; pentaerythritol triacrylate; dipropylene glycol dimethacrylate; tripropylene glycol dimethacrylate; butanediol dimethacrylate; hexanediol dimethacrylate; trimethylol propane trimethacrylate; di-(3-methacryloxy-2-hydroxypropyl ether of bisphenol-A; di(2methacryloxyethyl ether of bisphenol-A; di(3-acryloxy-2-hydroxypropyl ether of bisphenol-A; di(2-acryloxyethyl ether of bisphenol-A; and the like.

35 [0030] To achieve the desired ink viscosity and crosslinking properties, typically the monomer composition contains a combination of diacrylic and triacrylic monomers along with a monomer containing a single terminal ethylenic group, as illustrated in the examples which follow.

40 [0031] When the inks of this invention contain an oligomeric or polymeric material, said materials typically possess ethylenic unsaturation which can react with the ethylenically unsaturated monomers. Representative of such oligomers are acrylated epoxy resins; acrylated polyurethanes; acrylated polyesters; and the like.

45 [0032] The inks of the present invention may also contain a preformed polymer such as an acrylic polymer or copolymer of C₁-C₄ alkyl acrylates or methacrylates, or acrylic or methacrylic acid, vinyl polymers and copolymers such as polyvinyl chloride, polyvinyl acetate, polyvinyl alcohol, polyvinylpyrrolidone, cellulosic polymers and copolymers; and the like.

Polymerization Initiating System

50 [0033] Unless the ink is formulated specifically for use with EB or thermal curing, it will typically contain a polymerization initiating system activatable by actinic radiation, such as UV radiation. Such a photoinitiator system has one or more compounds that directly furnish cations or free radicals when activated by actinic radiation. The photoinitiator system may also contain a sensitizer that extends the spectral response into the ultraviolet, visible and near infrared spectral regions. Cationic polymerization photoinitiating systems typically are used to initiate ring opening polymerization in systems such as the epoxy compositions described herein. Such cationic photoinitiating systems include all substances which liberate Lewis acids or Brønsted acids upon exposure to actinic radiation such as UV radiation. Cationic photoinitiating systems which are particularly useful in the energy curable inks of this invention are arylsulfonium salts, especially the triarylsulfonium salt such as triarylsulfonium

phosphate, triarylsulfonium antimonate, triphenylsulfonium hexafluorophosphate, and diarylsulfonium salt; and aryl-iodonium salts, such as diaryliodonium hexafluoroantimonate, bisdodecylphenyliodonium hexafluoroantimonate, and the like. Such cationic photoinitiators may be used individually or in combination to effect suitable curing of the ink. Preferred are diaryl-iodonium hexafluoroantimonate and (n⁵-2,4-cyclopentadien-1-yl) [(1,2,3,4,5,6-n) (1-methylethyl) benzene]-iron hexafluorophosphate.

[0034] In free radical initiated curing systems such as the UV curable inks disclosed herein,, typically irradiation of a photoinitiator produces free radicals that initiate polymerization. A wide variety of photoinitiators may be used in the energy curable inks of this invention a few are described by B.M. Monroe and G.C. Weed in Photoinitiators for Free-Radical-Initiated Photoimaging Systems, Chem. Rev. 93, pp. 435-448 (1993) incorporated thioxanthone, ethyl 4-(dimethylamino) benzoate, alpha amino acetophenone, and Michler's ketone.

Adjuvants

[0035] The radiation curable inks of this invention may optionally contain the usual adjuvants to adjust ink flow, surface tension, surface penetration and gloss of the cured printed ink. Such adjuvants contained in the ink typically are a surface active agent, a wax, a humectant or a combination thereof. These adjuvants may function as leveling agents, wetting agents, dispersants, defrothers or deareators, or additional adjuvants may be added to provide a specific function. Preferred herein by reference. Preferred are isopropyl adjuvants include fluorocarbon surfactants such as FC430, available from the 3M Company; silicones such as DC57, available from the Dow Chemical Corporation; polyethylene wax; polyamide wax; polytetrafluoroethylene wax; and the like.

Printing Ink Formulation

[0036] The solvent-free, energy curable ink preferably contains as its essential ingredients typically about 2 to about 15% by weight of the ink of pigment, about .1 to about 10 % by weight of the ink of the rheological additive and the balance being the liquid energy curable vehicle which is substantially free of a fugitive solvent. The energy curable liquid vehicle typically comprises, one or more low molecular weight mono-functional or multi-functional monomers. For offset inks and other inks which require higher viscosities (>1,000 cps), a resin, a reactive oligomer or polymer may also be present. In addition to the essential ingredients the energy curable ink may also contain up to about 6 % by weight of the ink of the polymerization initiating system activatable by actinic radiation; and up to about 10 % or less by weight of the ink, of the surface active agent, a wax, humectant or combination thereof.

[0037] The primary advantage offered by the solvent-free, energy curable ink of this invention is that the rheology may be readily adjusted to provide an ink viscosity anywhere between about 3 cps and about 2,000 cps at 240 s⁻¹ and 25°C, simply by adjusting the ratio of the various types of monomer component, and/or by adjusting the ratio of pigment and rheological additive to liquid vehicle; and/or by adjusting both ratios.

[0038] The ink may be prepared by any conventional mixing and milling method typically used for preparing printing inks. Typically, the pigment and rheological additive are mixed with the liquid vehicle then milled. After milling additional liquid vehicle and any desirable adjuvants are optionally added and mixed to produce the energy curable ink. As indicated the above mentioned ratios are adjusted to achieve a printing ink with the desired viscosity, flow, color density, and curing characteristics. The ink formulation process is more fully described in the examples.

Method of Printing and Curing

[0039] This invention is also directed to a method of printing and curing an ink image comprising the steps: (a) providing a solvent-free energy curable ink of this invention as described supra; (b) printing the ink on a substrate surface to form an image; and (c) subjecting the image to actinic radiation or thermal energy to form a cured ink image.

[0040] The method of this invention is particularly directed to printing operations requiring very low viscosity inks such as for example gravure and flexographic printing. It is understood, however, that any suitable printing and curing means may be used to print and cure the solvent-free energy curable ink of this invention. Such suitable means include but are not limited to conventional gravure or flexographic printing presses, equipped with UV and/or EB curing stations which follow the printing station. Thus when the energy curable ink is free of a photoinitiator it may be cured by actinic radiation which is a beam of electrons. Alternatively, when the energy curable ink contains a polymerization initiating system, it may be cured by actinic radiation which is UV radiation. The printed energy curable ink containing a polymerization initiating system may be initially subjected to UV radiation and subsequently to a beam of electrons or thermal energy to complete the cure. As used herein the thermal energy is

intended to include radiant energy such infrared or microwave energy and the like; or conductive thermal energy such as that produced by a heated platen or hot air oven, for example.

[0041] The following examples illustrate specific aspects of the present invention and are not to limit the scope thereof in any respect and should not be so construed. In the following examples all percentages provided are in volume percent unless otherwise noted.

Example 1

[0042] An energy curable, cationic ink formulation was formulated using a modified Pigment Yellow 12 composition containing Pigment Yellow 12 and Theological additive. 20 Modified Pigment Yellow 12 composition containing Pigment Yellow 12 and rheological additive was prepared as described in Example III of U.S. Patent 5,062,894. A mixture of 16.5 parts of isatoic anhydride (96% pure) and 220 parts of a primary amine-terminated poly (ethylene oxide/propylene oxide) (70/30) copolymer having a number average molecular weight of approximately 2,000 (available from the Huntsman Corporation) was stirred and heated gradually to 80°C until evolution of CO₂ ceased. The infrared spectrum indicated that the isatoic anhydride had completely reacted as evidenced by the disappearance of the characteristic anhydride absorptions at 1748 cm⁻¹. Thereafter, 16.5 parts of t-butyl acetoacetate were added and the reaction mixture was heated at 95°C and stirred for 8 hours to form Agent 1.

[0043] Tetrazotized 3,3'-O-dichlorobenzidine (DCB) was then prepared by adding 21.7 parts DCB to 39.8 parts of 200 Be hydrochloric acid and 140 parts of ice/water mixture with constant stirring to form a homogenous suspension. 32.6 parts of a 38% solution of sodium nitrite was added to the suspension and stirring was continued for 1 hour 0-3°C. The excess nitrous acid was then destroyed by the addition of approximately 0.5 part sulfamic acid.

[0044] A fine suspension of coupler was prepared by charging 31.1 parts acetoacetanilide and 0.5 part phenylmethyl pyrazolone (a shading agent) to 400 parts water and 33.6 parts of 50% sodium hydroxide. The mixture was stirred until all solids were dissolved, then the temperature was adjusted between 0 and 5°C and thereafter the coupler was precipitated by slowly adding 36.2 parts of 70% acetic acid. Immediately prior to coupling, 20.6 parts of Agent 1 were added to the coupler suspension as stirring was maintained throughout coupler preparation and reaction.

[0045] Coupling was then carried out by adding the solution of tetrazotized DCB to the fine suspension of coupler over a 40 minute period while stirring until no excess tetrazotized DCB remained. Then the temperature was increased to 40°C. The resulting pigment slurry was stirred an additional 30 minutes, filtered, washed and dried in an oven at 75°C. (Yield 69 parts of Modified Pigment Yellow 12 composition containing Pigment Yellow 12 and rheological additive).

[0046] An energy curable, cationic ink was formulated from the following components.

COMPONENTS	WEIGHT %
Cyracure® 6110 ^(a) , 6110 ^(a)	65.5
Modified Pigment Yellow 12	15
CD 1012 ^(b)	3
Heloxo® 116 ^(c)	15
PE wax ^(d)	1
DC ^(e)	5

(a) Cyracure® 6110, available from the Union Carbide Corporation, is 3,4-epoxycyclohexylmethyl-3,4-epoxycyclohexylcarboxylate

(b) CD 1012, available from the Sartomer Corporation, is diaryliodonium of hexafluoroantimonate

(c) Heloxo 1-16, available from the Shell Chemical Company, is 2-ethylhexylglycidyl ether,

(d) PE wax, available from the Shamrock Corporation, is polyethylene wax

(e) DC57, available from the Dow Chemical Corporation, is silicone additive

[0047] The Cyracure® 6110 and the Modified Pigment Yellow 12 were mixed at high speed (about 1000 rpm) with a Cowles blade then processed through a media mill containing 1 mm size media. After processing the remaining components were added and the viscosity of the two inks were measured.

PIGMENT	VISCOSITY @ 25°C
Modified PY-12	300±50 cps at 240 s ⁻¹

EP 0 984 045 A1

PIGMENT	VISCOSITY @ 25°C
Conventional PY-12	1500±200 cps at 240 s ⁻¹

5

[0048] Printing runs were carried out with the modified ink on a F-1 printability tester from IGT Reprotest. The tester was equipped with a UV radiation unit and a lamp having an output of 200 Watt/inch in the UV spectral region and a cylindrical reflector. The major elements of the tester are: a plate cylinder with a replaceable photopolymer flexographic plate; an anilox roller for applying ink to the plate cylinder; a doctor blade assembly for regulating the ink supplied to the anilox roller; a rubber printing cylinder which along with the plate cylinder, forms a nip through which a substrate 5 carrier passes. The flexographic plate was an Epec® photopolymer plate a product of Polyfiberon. The substrate which was printed was polyester label film (available from Fasson) having a gloss of 67. When printing this film, the anilox roller was steel and had 80 line/cm and a cell volume 17.5 M¹â/M²â. The inking pressure between the anilox and the plate was adjusted to be 250 N and the printing pressure between the plate and the printing cylinder was 250 N. The printing speed was 1 m/sec.

[0049] The following parameters were measured to assess the quality of the printed image: optical density was measured with an XRite® 418 densitometer; and gloss was measured with a BYK portable glossmeter at a 60° angle using the statistical mode. Using modified Pigment Yellow 12 ink composition, the ink was applied to the substrate and cured with this apparatus. A cured ink film was likewise printed using conventional Pigment Yellow 12 ink composition.

[0050] Color density and Gloss measurements were also carried out with the modified Pigment Yellow 12 and conventional Pigment Yellow 12 prints. The assessed quality using the two ink formulations were:

25

PIGMENT	COLOR DENSITY	GLOSS 60°
Modified PY-12	1.44	87
Conventional PY-12	1.00	59

30

[0051] The ink containing the modified Pigment Yellow 12 has 35 better transfer onto the substrate due to lower viscosity and better flow. As a result, the print has more uniform ink lay, higher density and gloss than does the ink containing the conventional pigment.

Example 2

[0052] An energy curable, cationic ink formulation was formulated using a modified Pigment Blue 15.4 composition containing copper phthalocyanine blue pigment and Theological additive.

[0053] A rheological additive was prepared by charging a presscake, containing 210 parts by weight of copper phthalocyanine sulfonyl chloride (which may be prepared by any conventional method) into a mixture of 692 parts by weight of a primary amine-terminated poly (ethylene oxide/propylene oxide) (5/95) copolymer having a number average molecular weight of approximately 2,000 (available as XTJ 507 from the Huntsman Corporation) and 66 parts by weight of sodium carbonate and mixed. The final reaction mixture was then heated to 80-90°C under vacuum to remove water and produce the copper phthalocyanine additive.

[0054] The modified Pigment Blue 15.4 composition was prepared by combining 12 % by weight of the copper phthalocyanine derived rheological additive where P is the residue of copper phthalocyanine with 79% by weight of conventional Pigment Blue 15.4 during the attrition process step of the conventional pigment.

[0055] The energy curable, cationic ink was formulated from the following components.

55

COMPONENTS	WEIGHT %
Cyarcure® 6110 ^(a) â	15
Modified Pigment Blue 15.4	5
CD 1012 ^(b) â	2
Irgacure® 261 ^(c) â	.5

EP 0 984 045 A1

COMPONENTS	WEIGHT %
DVE 3 ^(a)	76
PE wax ^(d)	1
DC 57 ^(e)	.5

(a) Cyacure® 6110, available from the Union Carbide Corporation, is 3,4-epoxycyclohexylmethyl-3,4-epoxycyclohexylcarboxylate

(b) CD 1012, available from the Sartomer Corporation, is diaryliodonium of hexafluoroantimonate

(d) PE wax, available from the Shamrock Corporation, is polyethylene wax

(e) DC57, available from the Dow Chemical Corporation, is silicone additive

(f) Irgacure® 261, available from the Ciba Corporation, is $\text{h}\nu$

-2,4-cyclopentadien-1-yl)[(1,2,3,4,5,6-N)(1-methyl ethyl)benzene I-iron-hexafluorophosphate (-1)

(g) DVE, available from the GAF Corporation, is triethylene- glycol divinyl ether

[0056] The Cyacure® 6110 and the modified Pigment Blue 15.4 were mixed at high speed (about 2000 rpm) with a Cowles blade and then processed through a media mill containing 1 mm size media. After processing the remaining components were added and the viscosity of the two inks were measured.

PIGMENT	VISCOSITY @ 25°C
Modified PB-15.4	20±5 cps at 240 s-1
Conventional PB-15.4	100±20 cps at 240 s-1

Printing runs were carried out with a gravure hand-proofer from Pamarco Inc. The major elements of the gravure hand-proofer are: a 300 line/inch (118 line/cm) anilox roller; and a doctor blade assembly for regulating the ink supplied to the anilox roller. The printed samples were passed through a UV curing unit from R.P.G. Industries having a lamp with an output of 400 Watts/inch in the UV spectral region and- a cylindrical reflector. The substrate which was printed was the polyester label film from Fasson. The printing speed was about 1 m/sec (200 ft./min.) Using modified Pigment Blue 15.4 ink composition, a uniform ink film was applied to the substrate with the hand proofer and cured with this curing unit. A cured uniform ink film was likewise printed using conventional Pigment Blue 15.4 ink composition.

[0057] Color density and gloss measurements as described in Example 1 were carried out with the modified and the conventional Pigment Blue 15.4 prints. The assessed quality using the two ink formulations were:

PIGMENT	COLOR DENSITY	GLOSS 60°
Modified PB-15.4	1.4	90
Conventional PB-15.4	1.1	70

The ink containing modified Pigment Blue 15.4 demonstrates more uniform lay and less reticulation than the ink containing the conventional pigment, which results in higher density and better gloss of the print.

Example 3

[0058] An energy curable, cationic ink formulation was formulated using a modified Pigment Violet 23 composition containing Pigment Violet 23 and rheological additive.

[0059] Modified Pigment Violet 23 composition was prepared by combining 15 % by weight of the copper phthalocyanine derived rheological additive of Example 2 with 85% by weight of conventional Pigment Violet 23 during the attrition process step of the conventional pigment.

[0060] The energy curable, cationic ink was formulated from the following components.

EP 0 984 045 A1

COMPONENTS	WEIGHT %
Cyracure® 6110 ^(a)	26
Modified Pigment Violet 23	8
E6250 ^(h)	60
CD 1012 ^(b)	5
PE wax ^(d)	1
DC 57 ^(e)	.5

(a) Cyracure® 6110, available from the Union Carbide Corporation, is 3,4-epoxycyclohexylmethyl-3,4-epoxycyclohexylcarboxylate

(b) CD 1012, available from the Sartomer Corporation, is diaryliodonium of hexafluoroantimonate

(d) PE wax, available from the Shamrock Corporation, is polyethylene wax

(e) DC57, available from the Dow Chemical Corporation, is silicone additive

(h) E6250, available from the Hüls America Corporation, is (2-(3,4-epoxycyclohexyl)-ethyltrimethoxysilane)

[0061] The Cyracure® 6110 and the modified Pigment Violet 23 were mixed at high speed (about 1000 rpm) with a Cowles blade and then processed through a media mill containing 1 rvm size media. After Processing the remaining components were added and the viscosity of the two inks were measured.

PIGMENT	VISCOSITY @ 25°C
Modified PV-23	20±5 cps at 240 s ⁻¹
Conventional PV-23	150±50 cps at 240 s ⁻¹

[0062] Printing runs, as describe in Example 2, were carried out with the modified Pigment Violet 23 and compared to conventional Pigment Violet 23. Color density and gloss measurements were carried out with the modified and conventional Pigment Violet 23 prints. The assessed quality using the two ink formulations were:

PIGMENT	COLOR DENSITY	GLOSS 60°
Modified PV-23	2.34	75
Conventional PV-23	1.88	46

[0063] Poor flow of the ink containing conventional Pigment Violet 23 causes severe reduction of gloss.

Example 4

[0064] An energy curable, cationic, green ink formulation was formulated using the modified Pigment Yellow 12 of Example 1 and conventional Pigment Blue 15:3.

[0065] The energy curable, cationic ink was formulated from the following components.

COMPONENTS	WEIGHT %
Cyracure® 6110 ^(a)	64.5
Modified Pigment Yellow 12 of Example 1	6
Pigment Blue 15.3	10
CD 1012 ^(b)	3
Heloxy ^(g) 116 ^(c)	15

EP 0 984 045 A1

COMPONENTS	WEIGHT %
PE wax ^(d)	1
DC -57 ^(e)	.5

(a) Cyracure® 6110, available from the Union Carbide Corporation, is 3,4-epoxycyclohexylmethyl-3,4-epoxycyclohexylcarboxylate

(b) CD 1012, available from the Sartomer Corporation, is diaryliodonium of hexafluoroantimonate

(c) Heloxo 1-16, available from the Shell Chemical Company, is 2-ethylhexylglycidyl ether,

(d) PE wax, available from the Shamrock Corporation, is polyethylene wax

(e) DC57, available from the Dow Chemical Corporation, is silicone additive

(g) DVE, available from the GAF Corporation, is triethylene- glycol divinyl ether

[0066] The Cyracure® 6110, the modified Pigment Yellow 12, and the conventional Pigment Blue 15.3 were first mixed at high speed (about 1000 rpm) with a Cowles blade and then processed through a media mill containing 1 mm size media. After processing the remaining components were added and the viscosity of the two green inks were measured.

PIGMENT	VISCOSITY @ 25°C
Modified Green Ink	550±50 cps at 240 s ⁻¹
Conventional Green Ink	750±50 cps at 240 s ⁻¹

Example 5

[0067] An energy curable, free radical, addition polymerizable ink formulation was formulated using a modified Pigment Red 22 containing Pigment Red 22 and rheological additive.

[0068] Modified Pigment Red 22 composition containing Pigment Red 22 and rheological additive was prepared as described in Example 5 of U.S. Patent 5,024,698. 20.2 parts of 5-nitro-o-toluidine were dissolved in 280 parts water and 42.7 parts 31% hydrochloric acid at 65°C. The volume was adjusted to 600 parts at 3 to 5°C using ice/water, and 24.6 parts of aqueous sodium nitrite solution were added. The solution was stirred for 60 minutes at 5 to 7°C. 20.8 parts of 70% acetic acid were then added to the resultant diazo solution and the final volume was adjusted to 700 parts with the addition of ice/water.

[0069] 34.7 parts of 2-naph-L-halenecarboxamide, 3-hydroxy-N-phenyl (Naphthol AS) were dissolved in 600 parts water and 30 parts of 50% sodium hydroxide solution at 75°C. 2.0 parts of sulfated castor oil were added and the volume was adjusted to 1300 parts at 30°C.

[0070] The diazo solution was then added to the Naphthol AS solution over 25 minutes, together with 10.8 parts of azomethine coupler B of U.S. Patent 5,024,698. The mixture was stirred for 30 minutes to complete coupling and the resultant pigment slurry was heated to 90 OC., filtered, washed, and dried at 70°C. (Yield 65.7 parts of the modified Pigment Red 22 composition)

[0071] The energy curable, cationic ink was formulated from the following components.

COMPONENTS	WEIGHT %
Ebecryl® 3701 ^(a)	30
Trimethylolpropane triacrylate (TMPTA)	26.5
Modified Pigment Red 22	15
Tripropylene glycol diacrylate (TRPGDA)	12
N-vinyl pyrrolidone (N-VP)	10
Isopropyl thioxanthone (ITX)	3
Ethyl 4-(dimethylamino) benzoate (EDB)	3
Irgacure® 369 ^(b)	2
PE wax ^(d)	1

EP 0 984 045 A1

COMPONENTS	WEIGHT %
FC-430 ^(k)	0.5

(d) PE wax, available from the Shamrock Corporation, is polyethylene wax

(i) Ebecryl® 3701, available from the Radcure Corporation, is acrylated epoxy resin

(j) Irgacure® 369, available from the Ciba Corporation is, alphaamino acetophenone

(k) FC-430, available from the 3M Company, is a 40 fluorocarbon surfactant

[0072] The Ebecryl® 3701, TMPTA and the Modified Pigment Red 22 were mixed at high speed (about 1000 rpm) with a Cowles blade and then ground on a 3 roll mill. After grinding the remaining components were added and the 5 viscosity of the two inks were measured.

PIGMENT	VISCOSITY @ 25°C
Modified PR-22	500±50 cps at 240 s-1
Conventional PR-22	800±50 cps at 240 s-1

[0073] Printing runs as described in Example 1 were carried out with the modified and conventional Pigment Red 22 ink compositions except that a Cyrel® flexographic printing plate, available from E.I. du Pont de Nemours & Company, was used. Color density and gloss measurements were carried out with the modified and conventional Pigment Red 22 prints. The assessed quality using the two ink formulations were:

PIGMENT	COLOR DENSITY	GLOSS 60°
Modified PR-22	1.73	85
Conventional PR-22	1.52	60

[0074] The ink containing the modified Pigment produced higher density and gloss than the ink containing the conventional pigment.

Example 6

[0075] An energy curable, free radical addition polymerizable ink formulation was formulated using a modified Pigment Orange 16 containing Pigment Orange 16 and rheological additive.

[0076] Modified Pigment Orange 16 composition containing Pigment Orange 16 and rheological additive was prepared as described in Example 8 of U.S. Patent 4,946,509, but with Jeffamine M2005 in place of Jeffamine M2070. Tetrazotized o-dianisidine was prepared by charging 20.9 parts of o-dianisidine to 39.8 parts of 200 Be HCl and 140 parts of an ice/water mixture with constant stirring to form a homogeneous suspension. Then 32.6 parts of 38% sodium nitrite was added and stirring continued for 1 hour at 0 to 5°C. The excess nitrous acid was destroyed by adding approximately 0.5 parts sulfamic acid.

[0077] A fine suspension of acetoacetanilide (AAA) was prepared by adding 31.7 parts AAA to 400 parts H2O and 33.6 parts of 50% aqueous NaOH. The mixture was stirred until all of the AAA was dissolved. The temperature of the solution was adjusted to 0 to 5° C by adding ice and subsequently the AAA was precipitated by slowly adding 38.5 parts of 70% acetic acid.

[0078] An azomethine coupling component was formed by adding 1.2 parts of AAA to 13.5 parts of Jeffamine M-2005 and heating the mixture between 100 and 105°C while stirring. After 1 hour, the reaction was complete as evidenced by the disappearance of the ketone absorption band in the IR spectrum at approximately 1673 cm⁻¹. The resulting azomethine was added to the suspension of AAA immediately prior to coupling with the tetrazotized DCB. Coupling was then carried out by adding the tetrazotized DCB to the AAA suspension over a 1 hour period. Stirring was continued until no excess tetrazo remained. Then the slurry was heated between 90 and 95 °C, stirred for 15 minutes, filtered, washed and dried at 60°C. (Yield 62.2 parts of the modified Pigment Orange 16 composition).

EP 0 984 045 A1

[0079] The energy curable, free radical addition polymerizable ink was formulated from the following components.

COMPONENTS	WEIGHT %
Genomer® D 585 ^(m)	40
Glycerolpropoxy triacrylate (GPTA)	10
Modified Pigment Orange 16	15
Dipropylene glycol diacrylate (DPGDA)	26.5
ITX	3
EDB	3
Irgacure® 369 ^(j)	1
PE wax ^(k)	1
FC-430 ^(k)	.5

(j) Irgacure® 369, available from the Ciba Corporation is, alphaamino acetophenone

(k) FC-430, available from the 3M company, is a 40 fluorocarbon surfactant

(m) Genomer® D 585, available from Rahn Corporation, is an epoxy acrylate

[0080] The Genomer® D 585, GPTA and the modified Pigment Orange 16 were mixed at high speed (about 1000 rpm) with a Cowles blade then ground on a 3 roll mill. After grinding, the remaining components were added and the viscosity of the two inks were measured.

PIGMENT	VISCOSITY @ 25°C
Modified PO-16	900±100 cps at 240 s ⁻¹
Conventional PO-16	1,500±100 cps at 240 s ⁻¹

[0081] Printing runs as described in Example 5 were carried out with the modified and conventional Pigment Orange 16 ink compositions. Color density and gloss measurements were carried out with the modified and conventional Pigment Orange 16 prints. The assessed quality using the two ink formulations were:

PIGMENT	COLOR DENSITY	GLOSS 60°
Modified PO-16	2.00	91
Conventional PO-16	1.65	79

[0082] The ink containing the Modified Pigment produced a more transparent image with a cleaner shade and higher density and gloss, than did the ink containing the conventional pigment.

Example 7

[0083] An electron beam curable, free radical addition polymerizable ink formulation was formulated using the Modified Pigment Red 22 composition of Example 5.

[0084] The electron beam curable, cationic ink was formulated from the following components.

COMPONENTS	WEIGHT %
Ebecryl® 3701 ^(a)	38
Trimethylolpropane triacrylate (TMPTA)	26.5
Modified Pigment Red 22 of Example 5	15

EP 0 984 045 A1

COMPONENTS	WEIGHT %
Tripropylene glycol diacrylate (TRPGDA)	12
N-vinyl pyrrolidone (N-VP)	10
PE wax ^(d)	1
FC-430 ^(k)	.5

(d) PE wax, available from the Shamrock Corporation, is polyethylene wax

(i) Ebecryl® 3701, available from the Radcure Corporation, is acrylated epoxy resin

(k) FC-430, available from the 3M Company, is a 40 fluorocarbon surfactant

The Ebecryl® 3701, TMPTA and the modified Pigment Red 22 were mixed at high speed (about 1000 rpm) with a Cowles blade then ground on a 3 roll mill. After grinding, the remaining components were added and the viscosity of the two inks were measured.

PIGMENT	VISCOSITY @ 25°C
Modified PR-22	800±50 cps at 240 s ⁻¹
Conventional PR-22	1,200±100 cps at 240 s ⁻¹

[0085] The modified Pigment Red 22 ink formulation was used to print an image on of white polyethylene film with a gloss of using a Chestnut flexographic printing press with a Cyrel® Flexographic printing plate. The printing speed was 200 Feet/min (1 m/sec.). The printing press was equipped with an electron beam unit from ESI which had an irradiation output of 3 mega rads at 165 kV. The quality of the cured printed image was comparable to the UV cured image of Example 5 using white polyethylene film.

Example 8

[0086] The energy curable, free radical addition polymerizable ink formulation of Example 6 was used to print an image on white polyethylene film with a gloss of 40 using a Chestnut flexographic printing press with a Cyrel® flexographic printing plate. The printing speed was 200 feet/min (1 m/sec). The printing press was equipped with two curing stations through which the printed web passed. The first curing station through which the web passed as it left the printing station was a UV light unit from Prime Systems Inc. having a lamp with an output of 400 Watts/inch in the UV spectral region and a cylindrical reflector. The second curing station which was located after the first station along the path of the printed web, was a electron beam unit from which provided a beam of electrons having an irradiation output of 3 mega rads at 165 kV, which impinged on the printed surface of the web. The quality of the cured printed image was comparable to the UV cured image of Example 6 using white polyethylene film.

[0087] In practice the first curing step to UV radiation cures at least the surface of the printed ink image, and the second electron beam curing step cures the printed ink image in depth to complete the cure. By use of this hybrid curing step higher printing speeds are achieved with UV opaque ink systems. Also, better film properties, adhesion and less unreacted components are present that could migrate from the cured ink film.

Example 9

[0088] The energy curable, cationic ink formulation of Example 2 was printed on a SBS coated board having a gloss of 16, available from James River Corporation.

[0089] Printing runs were carried out as described in Example 2. Using the Modified Pigment Blue 15:4 ink 10 composition, a uniform ink film was applied to the substrate and cured. A cured uniform ink film was likewise prepared using conventional Pigment Blue 15:4 ink composition.

[0090] Color density and gloss measurements were carried out with the modified and conventional Pigment Blue 15:4 prints. The assessed quality using the two ink formulations were:

PIGMENT	COLOR DENSITY	GLOSS 60°
Modified P3-15:4	1.25	64

EP 0 984 045 A1

PIGMENT	COLOR DENSITY	GLOSS 60°
Conventional PB-15:4	1.03	52

[0091] The ink containing the modified Pigment produced a more uniform image with higher density and gloss on the coated 25 board, than the ink containing the conventional pigment.

Example 10

[0092] An energy curable, cationic ink formulation was formulated using a modified Pigment Black 7 composition containing Pigment Black 7 and rheological additive.

[0093] Modified Pigment Black 7 composition was prepared by dry mixing 19% by weight of the copper phthalocyanine derived rheological additive described in Example 2 with 81% by weight of conventional Pigment Black 7.

[0094] The ink was formulated from the following components.

COMPONENTS	WEIGHT %
Cyracure® 6110 ^(a)	65
Modified Pigment Black 7	18
CD 1012 ^(b)	5
Irgacure® 261 ^(f)	.5
DVE 3 ^(g)	5
PE wax ^(d)	1
DC 57 ^(e)	.5

(a) Cyracure® 6110, available from the Union Carbide Corporation, is 3,4-epoxycyclohexylmethyl-3,4-epoxycyclohexylcarboxylate

(b) CD 1012, available from the Sartomer Corporation, is diaryliodonium of hexafluoroantimonate

(d) PE wax, available from the Shamrock Corporation, is polyethylene wax

(e) DC57, available from the Dow Chemical Corporation, is silicone additive

(f) Irgacure® 261, available from the Ciba Corporation, is $(n^5\text{C}_4\text{H}_5)_2\text{Fe}$

-2,4-cyclopentadien-1-yl)[(1,2,3,4,5,6-N)(1-methyl ethyl)benzene I-iron-hexafluorophosphate (-1)

(g) DVE, available from the GAF Corporation, is triethylene- glycol divinyl ether

[0095] The Cyracure® 6110 and the modified Pigment Black 7 were mixed at high speed (about 2000 rpm) with a Cowles blade then processed through a media mill containing 1 mm size media. After processing, the remaining components were added and the viscosity of the two inks were measured.

PIGMENT	VISCOSITY @ 25°C
Modified PR-7	350±50 cps at 240 s ⁻¹
Conventional PR-7	700±50 cps at 240 s ⁻¹

[0096] Color density and gloss measurements were carried out with the modified and conventional Pigment Black 7 ink using the methods of Example 1. The assessed quality using the two ink formulations were:

PIGMENT	COLOR DENSITY	GLOSS 60°
Modified PB-7	2.02	78
Conventional PB-7	1.82	66

[0097] The ink containing the modified Pigment has a much higher density, gloss and better color jetness due to presence of the copper phthalocyanine derived rheological additive than the ink containing a conventional pigment.

[0098] Those skilled in the art having the benefit of the teachings of the present invention as hereinabove set forth, can effect numerous modifications thereto. These modifications are to be construed as being encompassed 5 within the scope of the present invention as set forth in the appended claims.

Claims

1. An energy curable ink comprising:

a pigment;

a rheological additive having the structure:




wherein P is the residue of an organic colorant, Y is a polyalkylene oxide moiety, U is a linking moiety covalently bonding Y to P, and s is an integer from 1 to 3 and; an energy curable liquid vehicle; wherein the ink is substantially free of a fugitive solvent.

2. The ink of claim 1 wherein the polyalkylene oxide moiety is an ethylene oxide polymer.

3. The ink of claim 1 wherein the polyalkylene oxide moiety is an ethylene oxide/propylene oxide copolymer.

4. The ink of claim 3 wherein the copolymer has the general formula:



wherein n is 4 to 400; each Q is independently H or CH₃, and Q' is a C₁-C₆ alkyl moiety.


5. The ink of claim 4 wherein n is 4 to 60.

6. The ink of any one of claims 1 to 5 wherein P is a residue of an azo pigment, phthalocyanine pigment, dioxazine pigment, quinacridone pigment, perylene pigment, or perinone pigment.


7. The ink of any one of claims 1 to 6 wherein U is a covalent bond, or a multivalent moiety selected from the group consisting of C₁-C₈ alkyl, -NHSO₂-, -O-, -CO-, -COO-, -N=, and -CONH-.

8. The ink of anyone of claims 1 to 7 where s has the value 1 or 2.


9. The ink of claim 1 wherein the rheological additive is an azomethine having the general formula:




wherein Y is the alkylene oxide polymer containing 4 to 200 groups; R and R^{1a} are independently selected from H, CH₃, OCH₃, OCH₂CH₃ and Cl; n is an integer from 1 to 5; X is selected from Cl, CH₃, and OCH₃; and Z is selected from 0 and N-Y, or an azomethine having the general formula:




wherein Y is the polyalkylene oxide polymer containing 4 to 20 repeat units; R^{1a} is H, CH₃, OCH₃, OCH₂CH₃ or Cl; n is an integer from 1 to 5; R^{2a} is CH₃ or COOCH₂CH₃; R^{3a} is H or CH₃; and X^{1a} is Cl or OCH₃, or a diarylide having the general formula:




wherein: R^{4a} and R^{5a} are independently selected from the C₁-C₄-alkyl, C₁-C₄ alkoxy, and halogen; m and p are independently integers of 0 to 5; X^{2a} is selected from Cl, CH₃, and OCH₃; U^{2a} comprises a divalent bridging moiety selected from C₁-C₈ alkyl, -NHSO₂-, -O-, -CO-, -COO-, and -CONH-; Y^{1a} comprises the polyalkylene oxide moiety having a number average molecular weight of about 200 to 10,000; and k and l are independently integers of 0 or 1, with the proviso that for at least 50 wt.% of the pigment composition, k and l are both equal to 0, and for at least 3 wt.% of the pigment composition 5 k and/or l are equal to 1 or an azomethine having the general formula:



wherein Y is the polyalkylene oxide polymer containing about 4 to about 20 repeat units; R⁶ is independently selected from Cl, OCH₃, CH₃, OC₂H₅, C₂H₅, and CONH₂; R⁷ is independently selected from Cl, OCH₃, CH₃, NO₂, OC₂H₅, C₂H₅, CONH₂, SO₃H, OH and COOH; and a and b are independently integers of 0 to 5 or a phthalocyanine having the general formula:



wherein Y has the general formula:



to wherein n is about 4 to about 400, and a, b, c and d are integers independently from about 0 to about 4, provided at least one of them is 1; each Q is independently H or CH₃ and Q' is a C₁-C₈ alkyl moiety.

10. The ink of any one of claims 1 to 9 wherein the pigment is selected from Pigment Yellow 1, Pigment Yellow 3, Pigment Yellow 12, Pigment Yellow 13, Pigment Yellow 14, Pigment Yellow 17, Pigment Yellow 37, Pigment Yellow 63, Pigment Yellow 65, Pigment Yellow 73, Pigment Yellow 74, Pigment Yellow 75, Pigment Yellow 83, Pigment Yellow 97, Pigment Yellow 98, Pigment Yellow 106, Pigment Yellow 114, Pigment Yellow 121, Pigment Yellow 126, Pigment Yellow 127, Pigment Yellow 136, Pigment Yellow 174, Pigment Yellow 176, Pigment Yellow 188, Pigment Orange 5, Pigment Orange 13, Pigment Orange 16, Pigment Orange 34, Pigment Red 2, Pigment Red 9, Pigment Red 14, Pigment Red 17, Pigment Red 22, Pigment Red 23, Pigment Red 37, Pigment Red 38, Pigment Red 41, Pigment Red 42, Pigment Red 112, Pigment Red 146, Pigment Red 170, Pigment Red 196, Pigment Red 210, Pigment Red 238, Pigment Blue 15, Pigment Blue 15:1, Pigment Blue 15:2, Pigment Blue 15:3, Pigment Blue 15:4, Pigment Green 7, Pigment Green 36, Pigment Violet 23, and Pigment Black 7.

11. The ink of claim 1 wherein the pigment is distinct from P.
12. The ink of claim 1 wherein the pigment is the same as P.
13. The ink of claim 12 wherein the ink contains an additional distinct pigment.
14. The ink of any one of claims 1 to 13 wherein the energy curable liquid vehicle is a ring opening polymerizable composition.
15. The ink of claim 14 wherein the polymerizable composition is a cationic polymerizable system comprising one or more mono-functional and/or multi-functional epoxide monomers.
16. The ink of claim 14 further comprising a polymerization initiating system activatable by actinic radiation.
17. The ink of any one of claims 1 to 13 wherein the energy curable liquid vehicle is a free radical addition polymerizable system comprising an ethylenically unsaturated monofunctional or multi-functional monomer.
18. The ink of claim 17 wherein the ink contains a free radical generating, addition Polymerization initiating system activatable by actinic radiation.
19. The ink of claim 1 wherein the ink additionally contains a surface active agent, a wax, or a combination thereof.
20. A method of printing and curing an ink image comprising the steps of:
- (a) providing an energy curable ink as defined in any of claims 1 to 19
 - (b) printing the ink on a substrate surface to form an image; and
 - (c) subjecting the image to actinic radiation or thermal energy to form a cured image.
21. The method of claim 20 wherein the actinic radiation is a beam of electrons.
22. The method of claim 20 wherein the energy curable ink contains a polymerization initiating system activatable by actinic radiation, and wherein the actinic radiation is ultraviolet radiation.
23. The method of claim 22 wherein the image is initially subjected to ultraviolet radiation and subsequently subjected to a beam of electrons or thermal energy.
24. The method of claim 23 wherein the thermal energy is radiant or conductive thermal energy.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 11 6822

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	US 5 176 745 A (MOORE PATRICK D ET AL) 5 January 1993 * column 2, line 29 - column 4, line 8 *	1,3,6-10	C09D11/00 C09D11/10 C09B67/00 C09B69/00
A	WO 92 13911 A (SUN CHEMICAL CORP) 20 August 1992 * page 1, line 10 - page 7, line 14 *	1-10,20	
A,D	US 4 946 509 A (SCHWARTZ RUSSELL J ET AL) 7 August 1990	1	
A,D	US 4 946 508 A (SCHWARTZ RUSSELL J ET AL) 7 August 1990	1	
A,D	DE 195 00 968 A (SCHMIDT GEB DRUCKFARBEN) 18 July 1996	1	
A,D	US 5 024 698 A (SCHWARTZ RUSSELL J ET AL) 18 June 1991	1	
A,D	US 5 062 894 A (SCHWARTZ RUSSELL J ET AL) 5 November 1991	1	TECHNICAL FIELDS SEARCHED (Int.Cl.6) C09D C09B
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 27 January 1999	Examiner Miller, A
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/82 (P4/C01)

EP 0 984 045 A1
ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 98 11 6822

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-01-1999

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5176745 A	05-01-1993	EP 0546857 A	16-06-1993
		JP 6009896 A	18-01-1994
		US 5310887 A	10-05-1994
WO 9213911 A	20-08-1992	US 5145997 A	08-09-1992
		AT 153041 T	15-05-1997
		CA 2103717 A	13-08-1992
		DE 69219760 D	19-06-1997
		DE 69219760 T	23-10-1997
		DK 572463 T	13-10-1997
		EP 0572463 A	08-12-1993
		ES 2102494 T	01-08-1997
US 4946509 A	07-08-1990	CA 2016539 A	23-11-1990
		DE 69007671 D	05-05-1994
		DE 69007671 T	14-07-1994
		DK 399458 T	24-05-1994
		EP 0399458 A	28-11-1990
		ES 2063193 T	01-01-1995
		JP 3009957 A	17-01-1991
		MX 171109 B	30-09-1993
		PT 94126 A, B	08-02-1991
US 4946508 A	07-08-1990	CA 2016539 A	23-11-1990
		DE 69007671 D	05-05-1994
		DE 69007671 T	14-07-1994
		DK 399458 T	24-05-1994
		EP 0399458 A	28-11-1990
		ES 2063193 T	01-01-1995
		JP 3009957 A	17-01-1991
		MX 171109 B	30-09-1993
		PT 94126 A, B	08-02-1991
DE 19500968 A	18-07-1996	WO 9621702 A	18-07-1996
		EP 0802954 A	29-10-1997
US 5024698 A	18-06-1991	AT 157690 T	15-09-1997
		CA 2078862 A	23-09-1991
		DE 69127540 D	09-10-1997
		DE 69127540 T	22-01-1998
		DK 524941 T	14-04-1998
		EP 0524941 A	03-02-1993
		ES 2107455 T	01-12-1997
		FI 923865 A	28-08-1992
		WO 9114744 A	03-10-1991

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

EP 0 984 045 A1
**ANNEX TO THE EUROPEAN SEARCH REPORT
 ON EUROPEAN PATENT APPLICATION NO.**

EP 98 11 6822

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
 The members are as contained in the European Patent Office EDP file on
 The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-01-1999

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5062894 A	05-11-1991	AT 150475 T	15-04-1997
		CA 2103718 A	13-08-1992
		DE 69218427 D	24-04-1997
		DE 69218427 T	23-10-1997
		DK 586391 T	08-09-1997
		EP 0586391 A	16-03-1994
		ES 2101091 T	01-07-1997
		WO 9213922 A	20-08-1992
<hr/>			

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82